



Article Mystic SD T3767

Method of Production	tufted	
Polmaterial	100 % 107	
Loops per unit area approx.	256.100 /m ²	
Dyeing	Fibre dyeing - Solution Dyed	
Backing material	Synthetics	
Backing	Textile back	
Pile weight approx.	1.850 g/m ²	
Total weight approx.	2.530 g/m ²	
Pile height approx.	11 mm	
Total height approx.	13 mm	
Delivery width	400 cm	
Repeat length		
Repeat width		
Qualification		<p>CE</p> <p>23</p> <p>JAB Teppiche</p> <p>HEINZ ANSTOETZ KG</p> <p>Dammheider Str. 67</p> <p>D-32052 Herford-Elverdissen</p> <p>EN 1307</p> <p>JT-CO-023-03</p> <p>EN 14041:2018-05</p> <p>Notified Body: 2401</p> <p>Floor covering to be used within a building</p> <p>* In loosely laid condition</p>
Color fastness / light fastnes	ISO 105-B02: 8	
Abrasion resistance wet / dry	ISO 105-X12: 5	
Water fastness	ISO 105-E01: 5	
Fastness to seawater		
Fastness to chlorine water		
resistance to heat conduction	ISO 8302 : 0,13 m ² /KW	
Standard of flammability	EN 13501-01 Cfl-s1 In loosely laid condition	
Absorption of step sound	EN ISO 140-8: 29 dB	
Sound absorption coefficient	α_w 0,20	
Moth protection		

We reserve the right to make any technical changes which serve to improve the products.

Version: 01.09.2023